


سازمان برنامه و بودجه

# مشخصات فنی عمومی کارهای بنائی

ماه ۱۳۵۳ سهر

نشریه شماره ۲۶

جمهوری اسلامی ایران



این نشریه پیش‌نویس مشخصات فنی عمومی برای کارهای بنایی می‌باشد و سومین  
نشریه ایست که در زمینه مشخصات فنی عمومی کارهای ساختمانی با استفاده از  
خدمات مهندسان مشاور تکنولوگ به دو زبان فارسی و انگلیسی تهیه شده است  
و ضمن قدردانی از خدمات کارشناسان موسسه مذکور در اختیار دستگاههای  
اجرایی و مهندسان مشاور قرار می‌گیرد .

امید است متخصصین فن با مطالعه این مشخصات نظریات اصلاحی خود را ابراز  
دارند که در تهیه متن نهائی مورد استفاده قرار گیرد .

دفتر تحقیقات و استانداردهای فنی



## فهرست مندرجات

### قسمت اول — مقررات کلی

<u>صفحه</u>	<u>شرح</u>	<u>ردیف</u>
۱	دامنه کار	۱-۱
۱	استانداردها و آئین نامه ها	۲-۱
۱ الی ۲	نمونه و آزمایش	۳-۱
۲	ارجحیت	۴-۱
۲	بازدید	۵-۱

### قسمت دوم — مواد اولیه بنائی

۳	سیمان برای بنائی	۱-۲
۳	ماسه برای بنائی	۲-۲
۳ الی ۴	مصالح سنگی برای ساختن بلوکها و بتنی	۳-۲
۴	آهک	۴-۲
۵	آب	۵-۲
۵	مواد فلزی برای مهار نمودن	۶-۲
۵ الی ۶	سنگ	۷-۲
۶	مواد رنگی برای ملات	۸-۲

### قسمت سوم — ملات های بنائی

۷	کلس	۱-۳
۸ الی ۹	مشخصات لازم ملات های بنائی	۲-۳



<u>صفحه</u>	<u>شرح</u>	<u>ردیف</u>
٩	تهیه، کاربرد و آزمایش ملاتهای بنایی	۲-۳
۱۰	قسمت چهارم - واحد های مصرفی در بنایی	۱-۴
۱۱	بلوکهای پیش ساخته بتنی	۲-۴
۱۲	بلوکهای بتنی توخالی باربر	۳-۴
۱۳	قسمت پنجم - بنایی با آجر	
۱۴	کلیات	۱-۵
۱۵	بنایی با آجرگلی معمولی	۲-۵
۱۶	قسمت ششم - بنایی با بلوك بتنی	
۱۷	کلیات	۱-۶
۱۸	بنایی با آجر توخالی	۲-۶
۱۹	قسمت هفتم - بنایی با سنگ	
۲۰	کلیات	۱-۷
۲۱	بنایی با سنگهای تراشیده	۲-۷
۲۲	بنایی با سنگ لاشه	۳-۷
۲۳	بنایی با سنگ بصورت خشکه چینی	۴-۷



## قسمت اول

### مق ررات گل

#### ۱- دامنه کار

- کارهای بنائی شامل تهیه کارگر، مصالح، وسایل و دستگاهها و انجام کلیه کارهای لازم برای اجرای کامل کارهای بنائی برطبق نقشه ها و مشخصات و براساس مقررات استاندار قرارداد با رضايت کامل دستگاه نظارت میباشد.

#### ۲- استانداردها و آئین نامه ها

- کلیه مصالح باید مطابق استانداردهای مربوطه ایران و همچنین سایر مطروقات مندرج در این مشخصات فنی - عمومی باشد. مصالحی که برای آن استاندارد ایرانی تهیه نشده ویا مصالحی که در این مشخصات فنی - عمومی ذکرنشده اند باید مطابق با استانداردهای بین المللی مورد قبول دستگاه نظارت باشد.

#### ۳- نمونه آزمایش

- کلیه مصالح و کارها شامل آزمایشات مندرج در این مشخصات فنی - عمومی ویا آزمایشات خواسته شده دیگر خواهد بود. پیمانکار باید در صورتیکه مهندس ناظر چنین دستور دهد، بهزینه خود تعدادارکانی نمونه برای تصویب در اختیار مهندس ناظر قرار دهد و استاندار و دلایل کافی نسبت به مناسب بودن مصالح و مرغوبیت کار را ائمه نماید. مصالح

## مقررات کلی

حمل شده بگارگاه که بهر چنان نامرفوب تراز نمونه های مورد تصویب باشند و یا بر طبق مشخصات نباشد مرد و شناخته شده و باید از محوطه کارگاه خارج شود .

### ۱-۴ ارجحیت

— هرگاه بین مندرجات این مشخصات فنی — عمومی و نقشه های مربوطه تناظر نداشته باشد ارجحیت آن مطابق مفاد ماده ۲ پیمان با نقشه های خواهد بود .

### ۱-۵ بازدید

— پیمانکار موظف است که تسهیلات لازم را جهت بازدید رئیس ستگاه نظارت در گلیه اوقات از کارگاهها ، انبارها ، و محل کار فراهم نماید . فراهم آوردن این گونه تسهیلات توسط پیمانکار به عیج وجه از مسئولیت های مخوله به او که در مدارک پیمان ذکر شده است نخواهد کاست .

## قصصت دوم

### مواد اولیه بناء

#### ۱- سیمان برای بنائی

الف - استاندارد ها و آئین نامه ها : استاندارد شماره ۹۵۸۹۰۱۳۹ ایران

ب - نوع سیمان : بجز درموارد یکه دستورد یگری مشخص شده باشد ، برای کارهای بنائی بالاتراز سطح زمین مجاور از سیمان نوع ۱ و برای پائینتر ازان سیمان نوع ۲ استفاده شود .

#### ۲- ماسه برای بنائی

الف - استاندارد ها و آئین نامه های اجرایی : استاندارد شماره ۹۹۵۶ ایران

ب - نگاهداری ماسه : ماسه باید بطريقی انبار گردش که امکان آمیخته شدن مواد خارجی با آن و پاضایع شدن آن نباشد . ماسه ضایع شده و یا آسوده را نباید در کارهای بنائی بکاربرد .

#### ۳- صالح سنگی برای ساختن بلوکهای بتقی

الف - استاندارد ها و آئین نامه های اجرایی : استاندارد شماره ۰۰۳۰۷۰ ایران

ب - سایر مشخصات : دانه بندی صالح سنگی که در ساختن بلوکهای بتقی بکار میروند نباید از حدود تعیین شده در جدول شماره ۱ تجاوز نماید .

مواد اولیه بنایی

ج - نگاهداری مصالح سنگی : باید مطابق آنچه درمورد نگاهداری ماسه برای بنایی دربند ۲-۲ بگفته شده باشد.

جدول شماره ۱ حدود رانه‌بندی مصالح سنگی

برای بلوکهای بتونی

درصد ریز ترازالمک (برحسب وزن)	اندازه الک میلیمتر	شطره الک
۱۰۰	۶/۵۲۰	۳/۸
۷۵-۹۰	۴/۷۶۰	۴
۳۵-۶۵	۲/۳۸۰	۸
۴۳-۵۲	۱/۱۹۰	۱۶
۱۵-۳۸	۰/۰۹۰	۳۰
۱۰-۲۵	۰/۲۹۷	۵۰
۲-۵	۰/۱۴۹	۱۰۰
۰-۳	۰/۰۷۵	۲۰۰

۴ آهک

الف - استانداردها و آئین نامه های اجرائی : استاندارد شماره ۲۷۰ ایران

ب - حمل و نقل و نگاهداری : آهک باید درسته هایی که آب قابل نفوذ در آنها نیست حمل و نقل شده و در مقابل رطوبت و مواد خارجی محافظت گردد. آهک باید حد اکثر ظرف ۵ روز پس از انبارشدن بکاررود. آهک شکفته نباید در صورتی نورآفتاب قرار گیرد و باید حد اکثر ظرف ۴ ساعت پس از اختلاط با آب مورد استفاده قرار گیرد.

## مواد اولیه بنائی

### ۵-۱ آب

الف - آبی که در ساختن ملاتهای حاوی سیمان پورتلند بکارمیروند باید مطابق مشخصات را داشته باشد در آئین کاربرد شماره ۳-۸-۱ موسسه استاندارد و تحقیقات صنعتی ایران باشد.

ب - آبی که برای ساختن ملاتهای بدون سیمان پورتلند بکارمیروند باید تمیز و عاری از مواد ضرر و خارجی باشد.

### ۶-۱ مواد فلزی برای مهار نمودن

الف - شبکه های فلزی : برای مهار نمودن و اتصال دیوارها باید از سیم گالوانیزه بضمانت حداقل ۳ میلیمتر ساخته شده و سوراخهای آن باید از یک سانتیمتر بزرگتر باشد.

ب - تسمه یا میله : برای مهار گردن و اتصال دیوارها باید از جنس خسته زنگ بوده و ابعاد و شکل آن مطابق جزئیات نقشه ها و یا مذکور رایین مشخصات فنی باشند.

### ۷-۱ سنگ

الف - سنگ باری : باید محکم، متراکم، یکپارچه و بار وام ویکرنگ باشد و در آن رگه های نامناسب، درز، شکاف و سایر ناقص استحکامی موجود نباشد. سنگ باید در مقابل عوامل جوی مقاوم باشد. سنگ باید از نوع مشخص شده در نقشه ها و یا سایر اسناد و مدارک قرارداد باشد. سنگ باید رای ابعاد خواسته شده و متناسب با کارمیوطه بود و نباید ضخامت آن از ۰.۲ سانتیمتر کمتر و از ۰.۷۵ سانتیمتر بیشتر باشد. سطح نمای سنگ باید مطابق مشخصات خواسته شده باشد. سنگ باید قبل از کارگذاری به ابعاد دقیق خواسته شده تراشیده شود.

## مواد اولیه‌بنائی

ب - سنگ لاسته : باید پکارچه، متراکم، و باد و ام و عاری از نقايس استحکامی و سطوح سائیده شده دور و فرسایش طبیعی باشد . سنگ لاسته نباید دارای خصائص کمتر از « ۱ سانتیمتر، عرضی کمتر از ۱/۵ برابر خاصت آن و طولی (جز برای سنگهای کله) کمتر از ۱/۱ برابر عرض آن باشد.

ج - سنگ برای قرنیز : (دریوش دیوار) ، کف پنجره وغیره باید دارای ابعاد نشان داده شده در روی نقشه ها باشد و باید کلیه مشخصات مربوط به سنگ مالوں و همچنین شرایط دیگر ذکر شده را دارا باشد .

## ۸-۲ مواد رنگی برای ملات

- مواد رنگی برای ملات باید از نوع اکسید های معدنی خالص، از نظر رنگ ثابت، شیمیائی ترکیب ناپذیر، و کامل "پودرشده و برای استفاده در ملات مناسب باشد .

### قسمت سوم

#### ملاتهاي بنائي

#### ۱-۳ گلیيات

الف - مصالح ونسبةهای اختلاط : ملاتهاي بنائي باید با نسبتهای از مصالح مشکله و به ترتیبی ساخته شود که ملات حاصله دارای مقاومت، یکنواختی، سهولت در کارآیی و سایر مشخصات خواسته شده بوده و مناسب برای کارمورد نظر باشد.

ب - مقاومت (استحکام) : ملاتها باید حداقل دارای مقاومت فشاری بمیزان نشان داده شده در جداول شماره ۲ و ۳ باشند. مقاومت ملات باید براساس روش نشان داده شده در استاندارد شماره ۱-۰-۲ اندازه گیری شود و نتایج آن به تصویب طهیند من ناظر بررسد و همچنین مطابق با مقادیر مشخص شده باشد.

ج - طبقه بندی ملاتها : طبقه بندی ملاتها بر حسب نسبت حجمی مندرج در نشریه شماره ۲۸ دفتر تحقیقات و استانداردهای فنی سازمان برنامه و پژوهش انجام میگیرد.

د - تعیین نوع و طبقه ملات : ملات باید از نوع و طبقه ای باشد که در نقشه ها و سایر استانداردها، قرارداد نشان داده شده است.

ملات هایی که مقاومت فشاری ۲۸ روزه آن ازه ۱ کیلوگرم بر سانتی‌متر مربع کمتر است باید فقط در کارهای بنائي داخلی و غیر بازی (تیفه) بکار بروند.

## ملاتهای بنائی

### ۲-۳ مشخصات لازم ملاتهای بنائی

الف - ملات ماسه سیمان : در جدول شماره ۲ مشخصات ونسبت

ترکیب مصالح مورد نیاز ملات ماسه سیمان شماره ۲ بطور اهنما

دارد است و مقدار سیمان داره شده در آین جدول حداقل

مقدار سیمان مصرفی برای نوع ملات مربوطه میباشد .

#### جدول شماره ۲

نوع ملات ماسه سیمان	نسبت ترکیب	مقادیر فشاری ۸ روزه			
		آب	سیمان پرتلند	ماسه شسته	لیتر
مترمکعب	کیلوگرم	کیلوگرم	کیلوگرم	نمونه	۲۰×۲۰×۲۰
ملات ۶ : ۱	۱/۰۳	۱۹۸	۲۵۶	۴۴	۲۰×۲۰×۲۰
" ۱ : ۵	۱/۰	۲۲۷	۲۶۵	۸۱	۲۰×۲۰×۲۰
" ۱ : ۴	۰/۹۹	۲۸۵	۲۶۱	۱۳۸	۲۰×۲۰×۲۰
" ۱ : ۳	۰/۹۴	۳۶۰	۲۵۸	۲۲۸	۲۰×۲۰×۲۰

ب - ملات ماسه آهک : در جدول شماره ۳ مشخصات ونسبت

ترکیب مصالح مورد نیاز برای ملات ماسه آهک داره شده

است .

#### جدول شماره ۳

نوع ملات ماسه آهک	نسبت ترکیب	مقادیر فشاری ۸ روزه		
		آب	ماسه خاکسی	پودر آهک شفته
مترمکعب	کیلوگرم	لیتر	کیلوگرم	نمونه
ملات ۱ : ۳	۰/۹	۱۷۴	۲۹۰	۲۰×۲۰×۲۰

ملاتهای بنائی

ج - ملات حرامزاره (باتارد) در جدول شماره ۴ مشخصات و نسبت ترکیب  
مصالح مورد نیاز ملات باتارد داره شده است.

جدول شماره ۴

نوع ملات	نسبت ترکیب	مقادیر متوسط فشاری				
		آب	سیمان	پودر آهک	پودر آهک شکنده	ماسه شسته
باتارد ۸:۲:۱	متراکم	کیلوگرم	کیلوگرم	کیلوگرم	لیتر	۲۰×۲۰×۲۰
باتارد ۱۰:۲:۱	متراکم	۱۱۰	۱۱۰	۱۳۱	۲۸۰	۲۵
باتارد ۱۰:۲:۱	متراکم	۱۱۰	۱۱۰	۱۳۱	۲۸۰	۲۸

۳-۳- تهیه، کاربرد و آزمایش ملاتهای بنائی

الف - استانداردها و آئین نامه های اجرائی : استاندارد شماره ۱-۲۰ ایران.

ب - سایر مشخصات : ملات باید بمقادیر تهیه شود که بتوان آنرا کلاً و در زمانی کوتاه بکاربرد . ملات ماسه سیمان حد اکثر تا ۳۰ دقیقه پس از مخلوط کردن باید بکار رود .

## قسمت چهارم

### واحد های صرفی درینائی

۱-۴ آج

الف - استاندارها و آئین نامه های اجرایی : استاندارد شماره ۷ ایران

ب - آجرهای غیر استاندارد : بگاربردن آجرهای محلی و معمولی که از نظر ابعاد و سایر مشخصات مطابق استاندارد شماره ۷ ایران نمیباشد در صورتی مجاز است که استفاده از آن در روی نقشه ها و یا توسط صهندس ناظر تصویب شده و همچنین شرایط زیر را دارا باشد :

۱ - آجر باید کاملاً پخته و یکپارچه و سخت باشد و همچنین عاری از تلهه پیچش، فرورفتگی و برآمدگی بوده و هرگاه بایک آجر به آجر یگری ضربه ای وارد آید صدای مشخص زنگ دارتولید کند.

۲ - آجر باید دارای ابعاد مشخص شده باشد و تغییرات ابعاد آن نباید از آنچه در استاندارد شماره ۷ ایران داده شده تجاوز نماید.

۳ - لبه های آجر باید مستقیم وزوایا و گوشه های آن کامل باشد.

۴ - آجر باید دارای مقاومت فشاری تعیین شده باشد . در هیچ صورت مقاومت فشاری متوسط آجرهای ماشینی نباید از ۰ . ۰ کیلوگرم بر سانتیمتر مربع و مقاومت فشاری هیچیک از آجرها بتنهای از ۰ . ۸ کیلوگرم بر سانتیمتر مربع کمتر باشد و مقاومت فشاری آجر فشاری نباید از ۰ . ۵ کیلوگرم بر سانتیمتر کمتر باشد .

۵ - میزان جذب آب آجر از مقادیر تعیین شده نباید بیشتر باشد .

ج - آجر نصا : باید علاوه بر این بودن مشخصات فوق الذکر دارای زنگ

## واحد های مصرفی درینا ئی

وظرفی باشد که در نقشه ها نشان داده شده و یا مهندس ناظر تصویب نموده است .

د - حمل و نقل و نگهداری : آجر باید بطريقی حمل و نقل شود که هیچگونه نقصانی که آنرا عاری از شرایط فوق الذکر نماید در آن حاصل نگردد .

## ۲-۴ بلوکهای بتني توخالی غیرباربر

الف - بلوکهای پیش ساخته بتني باید علاوه بر ارا بودن مشخصات ذکر شده در استاندارد شماره ۷۰ ایران شرایط ذکر شده دریند های قسمت ۲-۴ را نیز حائز باشد .

ب - بلوکهای بتني گه در محل کار ساخته میشود باید علاوه بر ارابون مشخصات ذکر شده در استاندارد شماره ۷۰ ایران شرایط زیر را نیز حائز باشد .

### ۱- نسبت اختلاطی مواد متشکله برای بلوکهای غیرباربر باید از مخلوط

ماسه درشت دانه و سیمان با نسبت جمعی ۴:۱ تهیه گردد .

( ۵ کیلوگرم سیمان + ۱۲٪ متر مکعب ماشه درشت دانه )

۲-  قالب گیری و تراکم بلوکها باید با استفاده از ماشینهای بلوک ساز از نوع وسایل و شرایط موردن قبول صورت گیرد .

۳-  بتن مصرفی در ساختن بلوک باید با مخلوط کن و بارعایت مندرجات بند ۲-۷ ساخته میشود .

۴- مقاومت فشاری متوسط بلوکها ( یا احتساب سطح سوراخها ) که براساس مندرجات استاندارد شماره ۷۰ ایران اندازه گیری میشود باید از ۴ کیلوگرم بر سانتیمتر مربع کمتر باشد .

## واحد های مصرفی درینا ئی

۵- سطح نمای بلوکها باید کاملاً صاف، یکنواخت و عاری از سوراخ، تمرکز نامتناسب رانهها، لخته شدن سیمان، لکه، تسلیک خوردگی، لمپریدگی و سایر نقصانات باشد. لبه بلوکها باید مستقیم و بد و نقص باشد.

۶- بلوکها صد م دیده : بلوکها ظیله در حین ساخت وحمل ونقل وبا هر زمان قبل از لارگاری صد م دیده آند برای استفاده در بنائی مجاز نمیباشند. وصله و تعمیر نمودن بلوکها آسیب دیده مجاز نمیباشد.

## ۳-۴ بلوکها بتنی توخالی باربر

الف - این قبیل بلوکها باید با درنظر گرفتن مقررات اضافی وبا موارد استثنایی زیر حاکیز شخصات ذکر شده دریند ۲-۴ بالا باشند.

۱- مقاومت فشاری متوسط بلوك (با احتساب سطح سوراخها) که مطابق استاندارد شماره ۰۷ ایران اند ازه گیری میشود نباید از ۰.۶ کیلوگرم بر سانتیمترمربع کمتر باشد.

۲- خاصامت بیواره های بلوك نباید هیچگاه از ۳ سانتیمتر کمتر باشد.

### قسمت پنجم

## بنایی با آجر

### ۱- گلیات

الف - شرط لازم در آجر کاری : انجام هرگونه بنایی با آجر در موافقی که گرمای هوای محل کار و یا درجه حرارت هر یک از موارد مصرفی ازه درجه سانتیگراد کمتر است مجاز نمیباشد مگراینکه وسایل کافی و مجاز برای حرارت را دن یا عایق نمودن محل کار و یا مواد مصرفی بکار رود به طوریکه درجه حرارت از مقدار مشخص شده بالا کاهش نیابد .

ب - آماده نمودن بستر زیرین : گلیه سطوح زیرین که گارهای بنایی بر روی آن آغاز میشود باید کاملاً تمیز شده و قبل از شروع کار مرطوب گردد .

### ج - ملات

۱ - ملات باید کاملاً در سطح جامد بستر زیرین و همچنین روی سطوح قائم آجرپیش شود .

۲ - ملات را باید بیش از اندازه لازم جلوتر از محل آجر کاری پخش نمود تا ملات قبل از قرار دادن آجر سفت نگردد .

۳ - ملات سخت شده که از روی داریست، گف و یا از صلتهاي دیگر برداشته شده باشد باید مورد استفاده قرار گیرد .

### ۲- بنایی با آجر فرشتاری

الف - خیساندن آجر : آجر باید قبل از نصب تمیز شده و کاملاً در آب خیسانده

## بنائی با آجر

شود و در حین ساختمان مرتضوب نگهداشته شود.

ب - طرز قرار گرفتن آجر و ترتیب آن : کارهای آجری باید با استفاده از روش پیووند بلوکی و صلیبی ساخته شود. برای دیوارهای آجری آرما توردار و یاد رمادر استثنای دیگری که درستگاه نظارت تشخیص دهد میتوان از پیووند محلی (روش کله - راسته) نیز استفاده نمود.

## ج - آجر چینی

۱ - آجر باید کاملاً "ترازیاب رزهای بضمایت مساوی و یکنواخت چید" شود. ضمایت بند های آجر کاری نمایاب باید حد اکثر ۱۲ میلیمتر و حداقل ۱ میلی متر باشد. آجر کاری حاصله باید کاملاً "شاقول" و مطابق با بعاز، جهت و محورهای نشان داره شده در نقشه ها باشد و سطح عمودی هر آجر را قبل از نصب باید بالایه های از ملات پوشانید و سپس با استفاده از ماله کمی در ملات فروبرده در محل خود جایگزین نمود.

۲ - آجر نصب شده نماید پس از سخت شدن و یا حتی خودگیری اولیه ملات در جای خود حرکت داره شود. جایگزینی نهایی آجر باید در زمانی صورت گیرد که ملات هنوز کاملاً "شل" است.

۳ - کارهای آجری زیرین تا ارتفاع ۳۵ سانتیمتر بالاتر از سطح زمین باید با استفاده از آجرهای انتخابی کاملاً "جامد و خوب پخته شده" انجام گیرد.

## بنائی پا آجر

۴— نما سازی آجر باید با استفاده از دیوار پشت بند صورت گیرد و سطح پشت آجر نما باید با یک لایه بعرض حداقل یک سانتیمتر ملات اندود شود بطوريکه روز بین آجر نما و آجر پشت بند کاملاً "با ملات پرشود" لیکن این عمل در محل آجر های نمای که به منظور قفل و بست بکار میروند قطع خواهد شد .

## ۵— قفل و بست در کارهای بنائی با آجر

۱— در موافقیکه آجر کاری در مجاورت ستون بتقni و یا فلزی قرار های میگیرد و در آن محل در زان بساط پیش بینی نشده باشد باید مهار فلزی از نوع عویشکل خواسته شده بفواصل لازم در داخل بند های آجر قرار گرفته و انتهای آن در داخل ستون مهار شده و یا با آن جوش شود .

۲— محل تقاطع دیوارهای متقطع وکلیه گوشه ها باید یکجا و یا بصورت لا ریز ساخته شوند . بنابراین باید دیوار چینی گوشه ها و محل تقاطع دیوارها و یا بطور کلی هر نقطه دیگری از دیوار در امتداد قائم متوقف شود . در محل تقاطع ها باید در دیوار متعامد را توسط میله های فلزی بصورت نبیش بهم پیوند دار .

## بنایی با آجر

### ۵ - مشخصات بند در آجرکاری

۱ - بند های نما باید هنگامی که ملات هنوز خمیری است با وسایل قابل قبول و کمی مقصر بند کشی گردد.

۲ - داخل کلیه بند های دیوارهای داخلی و خارجی که بعد از پوشیده و یا ناسازی می شوند باید بعمق کافی از ملات خالنسی و تمیز گردد.

۳ - بند کارهای آجری که بوسیله عایق پوشانیده می شوند باید تالب آجر با ملات پرسود.

### ۶ - محلهای باز در آجرکاری

۱ - محل نصب دروینجره و سایر محلهای باز در دیوارها باید بطور دقیق و با استفاده از آجرهای نیمه و یا آجرهای بریده شده با ندازه مورد نظر ساخته شود. آجر باید با ندازه های تعیین شده با استفاده از ارهای آجربری و یا سایر وسایل مورد قبول بطریقی بریده شود که سطوح و گنجهای محلهای باز در دیوار کاملاً صاف و شاقولی ساخته شده و همچنین از ایجاد شکستگی و یا ترک در آجرها جلوگیری شود.

۲ - در محل نصب دروینجره های خارجی، دیوار باید فاصله کافی با چهار چرب را شته باشد که بتوان در زمینه را با مواد انعطاف پذیر و عایق موردنظر پر نمود.

۳ - استفاده از آجر نیمه : آجر نیمه را می توان برای محلهای باز در دیوار و برای پر کردن پشت آجرهای راسته و سایر محلهای موردن تصویب بگارید مشروط براینکه سطح یا لبه آجر در محل نیمه شده بطرف داخل قرار گرفته و همچنانه قسمتی از نمای آجرکاری را تشکیل ندهد.

## بنائی با آجر

ح - دیوارهای دو جداره آجری : در ساختن چنین دیوارها مقترنات اضافی زیر باید رعایت گردد .

۱ - دیوارهای دو جداره باید بالاتراز سطح زمین اطراف و سرروی تکیه گاهی جامد شروع گردد .

۲ - بجز درموارد یکه نقشه‌ها ابعاد دیگری را نشان دهد عرض جدارهای داخلی و خارجی باید از  $\frac{1}{3}$  آجر کمتر و عرض فضای خالی بین دو دیوار باید از هشت سانتیمتر کمتر باشد و سانتیمتر بیشتر باشد .

۳ - جدارهای داخلی و خارجی باید با استفاده از مهارهای مستطیل شکل ( بشکل قاب ) که با استفاده از میله‌گرد ضد زنگباقطر حداقل ۸ میلیمتر ساخته می‌شود بیکدیگر اتصال داره شوند . مهارها باید بزرگتر از  $50 \times 50$  سانتیمتر بطور عمودی و  $60 \times 60$  سانتیمتر بطور افقی از یکدیگر فاصله داشته باشند و تعداد آین بسته‌ها هیچ‌گاه نباید در هر متر مربع دیوار از عدد کمتر باشد و محلهای بازو کنجهها باید مهارهای اضافی لازم تعبیه شوند .

۴ - در موارد یکه کوچکترین امکان نفوذ آب بداخل فضای بین دیوارها وجود دارد سوراخهای کوچک بشکل مدار باید در سطح زیرین دیوار تعبیه شود . برای انجام اینکار می‌توان تعدادی کافی میله روغن زده شده فلزی و یا لوله لاستیکی را در داخل ملات بند ها قرار داده و پس از خود گیری ملات خارج نمود . این سوراخها باید آبرا بطرف خارج ساختمان هدایت نموده و فاصله آنها از یکدیگر نباید از یک متر تجاوز نماید .

۵ - بالای دروینجره و سایر محلهای باز در دیوار و سطح روی فوندانسیون

## بنایی با آجر

که دیوار روی آن قرار میگیرد باید با استفاده از زرق گالوانیزه و یا مواد مورد قبول دیگر پوشانیده شود تا آبرابه خارج دیوار هدایت نموده و رطوبت را خل بین ویا در روپنجه نگردد.

۶- هیچگونه ریزش ملات بداخل جدار بین دیوارها مجاز نمیباشد برای جلوگیری از ریزش ملات میتوان از چوب یا تسمه که عرض آن مساوی با جدار بین دیوار باشد، استفاده نمود تا ملاتهای ریخته شده در روی آن جمع آوری و سپس خارج گردد.

## ط - تعمیر و نظافت

۱- وصله کاری و تضمیر بند های آجرکاری و یا پرگردن سوراخها باید با ملات تازه صورت گیرد.

۲- باید رقت شود که سطح آجرها با ملات آلوده و آفته نگردد.

۳- کلیه تکه های ملات که به آجر چسبیده اند باید پس از خشک شدن کامل ملات با استفاده از طاله و یا برس برداشته شوند.

۴- محافظت کارهای آجری : آجرکاری باید در صورت لزوم با استفاده از زورقها نایلونی و یا پوششها قابل قبول دیگر ر مقابل باران و برف و هرگونه عوارض جوی محافظت شوند. در هوای سرد که امکان یخ بندان میروند کارهای آجری باید پوشانیده شده و در صورت لزوم حرارت را در میشوند بطوریکه حرارتی بحداقل ۵ درجه سانتیگراد بمدت ۷۲ ساعت پس از نصب در کارهای آجری تائمهین گردد. در هوای گرم، آجرکاری که با ملات سیمانی ساخته شده باید بمدت کافی مرتب نگهدارشته شود.

### قسمت ششم

#### بنائی با بلوك بتني

#### ۱-۶ گلیات

الف - حرارت لازم : انجام هرگونه بنائی با بلوك بتني در موافقیکه گرمای هواي محل کار و يا درجه حرارت هر يك از مواد مصرفی ازه درجه سانتيگراد كمتر است مجاز نمیباشد مگر اينكه وسائل کافی و مجاز سراي حرارت دادن یا عایق نمودن محل و يا مواد مصرفی بكار رود بطوريکه درجه حرارت از مقدار مشخص شده بالا کاهش نیابد .

ب - آماره نمودن بستر زيرین : كليه سطوح زيرین که کارهاي بنائي برروي آن آغاز ميشود باید کاملاً تميز شده و قبل از شروع کار مرطوب گردد .

#### ج - ملات

۱ - ملات مصرفی باید ملات سيماني ازنوع مشخص شده باشد و باید کاملاً در سطح جامد بستر زيرین و همچنین روی جدارهاي قائم بلوك پخش گردد .

۲ - ملات را نماید بيش از اندازه لازم جلوتر از محل کار گذاشتен بلوكها پخش نمود تا ملات قبل از قراردادن آجر سفت نگردد .

۳ - ملات سخت شده که از روی داربست ، کف ، و يا اzmحلهاي دیگر برداشته شده باشد نماید مورد استفاده قرار گیرد .

#### ۶-۲ بنائي با بلوك توخالي

الف - خيساندن بلوك : بلوك باید قبل از نصب تميز شده و کاملاً در آب

بندایی با بلوک بتنی

خیسانده شود و در حین ساختمان مرطوب نگهداشته شود.

### ب - بلوک چینی

۱ - بجز در موارد یکه خصا است دیوار برای بلوک چینی بترتیب گل و راسته کافی است بلوک چینی باید با بلوکها ای صورت گیرد که عرض آن مساوی ضخامت دیوار باشد. مثلاً دیوار های ۳۰ سانتیمتری باید با بلوکها ای بعرض ۳ سانتیمتر ساخته شود.

۲ - بلوک باید کاملاً تراز چیده شود بطوریکه جدار بلوک و فضای خالی آن قائم باشد و درز عمودی رجهای متواالی یک در میان دریک امتداد قرار گیرد. تار حاصله باید کاملاً شاغل و مطابق با ابعاد، جهت، و محورهای نشان داده شده در نقشه ها باشد.

۳ - انتهای و گوشه دیوار را باید قبل از قسمتهای میانی چید بطوریکه پیوسته یا هرج بالاتراز رجهای میانی باشند.

۴ - ساختن دیوارهای بازپریا بلوک سیمانی فقط در صورتی مجاز است که در آنها آرماتور قائم کارگذاشته شود. تعداد و قطر آرماتورهای قائم در هر مورد باید با توجه به موقعیت دیوار محاسبه گردد. فضای خالی بلوکها در محل قرارگرفتن آرماتورهای قائم و همچنین در رجهای زیر تراز قطعی - زیر تیرها و زیر الها باید با ملات ماسه سیمان ۶:۱ پر گردد. سطح فوقانی دیوارهای بلوکی باید کاملاً عاری از ملات باشد تا ایجاد چسبندگی و قفل ویست کافی بین کف و دیوار ممکن گردد.

۵ - بلوک چینی باید بطوریکه نتوخت انجام شود بطوریکه در هر زمان هیچ قسمت از یک دیوار بیش از یکمتر از قسمتهای دیگر آن بالاتر نباشد.

۶ - بلوک نصب شده نباید پس از ساخت شدن و باحتو خود گیری

اولیه ملات درجای خود حرکت داره شود . جایگزینی نهائی بلوک

باید در زمانی صورت گیرد که ملات هستوز کاملاً "شل است .

۷- بلوک چینی نیمه تمام باید در حالت قطع شود که ایجاد قفل و بست

با بلوک چینی بعدی طبق آنچه در بندج خواهد آمد ممکن باشد .

قبل از آنکه بلوک چینی بعدی شروع گردد باید کلیه ملات اضافی

سست برداشته شود و بند های سطحی "باید کاملاً" با آب خیس

گردند .

### ج - قفل و بست در کارهای بنایی با بلوک بتی

۱- در مواقعيکه بلوک در مجاورت ستون بینی و یا فلزی قرار میگیرد و در آن

محل در زان بساط پیش بینی نشده باشد باید مهارهای فلزی از نوع

و بشکل خواسته شده طبق نقشه در داخل بند های دیوار قرار

گرفته و انتهای آن در داخل ستون مهار شده و یا با آن جوش شود .

۲- دیوارهای باربر متقطع و تیغه ها باید (بجز در کنج) باید یگر قفل

و بست شوند بلکه دودیوار باید بوسیله تسمه مهاریکه ضخامت آن

هرگز باید از ۶ میلیمتر و عرض آن از ۳ سانتیمتر و طول آن از ۶۰ سانتیمتر

کمتر باشد و د و انتهای آن بطور قائم باندازه ۵ میلیمتر خرم شده باشد

بیکد یگر اتصال داره شود . این تسمه های مهاری باید حد اکثر

در فواصل قائم ۱ / متری از یکد یگر قرار گیرند و د و انتهای خم شده آن

که در داخل فضای خالی بلوک قرار میگیرد باید با پر کردن فضای

خالی با ملات در محل استوار گردد .

۳- دیوارهای غیر باربر متقطع باید با استفاده از شبکه های سیمی

گالوانیزه که طول آن از ۴ سانتیمتر باید کمتر باشد ، یا کرج در میان

بیکد یگر متصل گردند .

## بنائی با بلوك بتني

### د - مشخصات بند در کارهای بنائی با بلوك بتني

- ۱ - کلیه بند های قائم باید کاملاً "باملات پرشود" .
- ۲ - درزهای بین بلوکها نمایند رهندگام بلوك چینی بند کشی نشد هباشند  
باید کاملاً "پاک گردند و سپس باملات بند کشی پوشوند" . ملات باید  
کاملاً "داخل درزها رانده شده و هنگامیکه ملات هنوز خمیری  
است با وسائل مورد قبول بصورت کمی مقصر بند کشی شود" .
- ۳ - داخل کلیه بند های دیوارهای داخلی و خارجی که بعد از  
پوشیده و یاناumasازی میشوند باید بعمق کافی از ملات خالی و تمیز  
گردد .
- ۴ - بند کارهای بلوك بتني که بوسیله عایق پوشانیده میشوند باید با  
سطح خارجی بلوك دریک سطح باشد .

### ه - محلهای باز در بلوك چینی

- ۱ - محل نصب دروینجره و سایر محلهای باز در دیوار باید بطور  
 دقیق و با استفاده از بلوکها نیمه ویا آجرهای بریده شده  
 باندازه سور در نظر ساخته شود . بلوك باید باندازه های تعیین  
 شده با استفاده از اره های مخصوصی ویا سایر وسائل مورد قبول  
 بطریقی بریده شود که سطوح و گنجهای محلهای باز در دیوار  
 کاملاً صاف و شاغلی ساخته شده و همچنین از ایجاد شکستگی  
 ویا ترک در آجرها جلوگیری شود .
- ۲ - در محل نصب دروینجره شای خارجی ، دیوار باید فاصله کافی  
 با چهار چوب را شته باشد تا بتوان در ز مریوطه را با مسوار  
 انعطاف پذیر و عایق مورد نظر پر نمود .

## بنائی با بلوک بتنی

و - دیوارهای دوجداره بلوکی : در ساختن چنین دیوارها مقیسر راست اضافی زیر باید رعایت گردد :

۱ - دیوارهای دوجداره باید از ترازیا لاترا زسطح زمین اطراف و سرروی تکیه گاهی جامد شروع شود .

۲ - بجز در موارد یکه نقشه ها ابعاد دیگری رانشان دهند عرض جدارهای داخلی و خارجی باید از ۱۰ سانتیمتر کمتر و عرض فضای خالی بین دو دیوار باید از ۸ سانتیمتر کمتر و از ۱۲ سانتیمتر بیشتر باشد .

۳ - جدارهای داخلی و خارجی باید با استفاده از مهارهای مستطیلی شکل که با استفاده از میله گرد ب قطر حداقل ۸ میلیمتر ساخته میشود بیکدیگر اتصال داده شوند . مهارها باید حد اکثر ۵ سانتیمتر بطور عمودی و ۶ سانتیمتر بطورافقی از یکدیگر فاصله داشته باشند و تعداد آینین بسته های شیپگاه باید در هر مترمربع دیوار از ۴ عدد کمتر نباشد . در محلهای بسازو گنجها باید مهارهای اضافی لازم تعبیه شوند .

۴ - در موارد یکه کوچکترین امکان نفوذ آب بداخل فضای بین دیوارها وجود دارد سوراخهای کوچک بشکل مدار باید در سطح زیرین دیوار تعبیه شود . برای انجام اینکار میتوان تعداد کافی میله روش زده شده فلزی و یا لوله لاستیکی را در داخل ملات بند ها قرار داده و پس از خودگیری ملات خارج نمود . آین سوراخها باید آبرا بطرف خارج ساخته امانه دایت نموده و فاصله آنها باید از یک متر تجاوز نماید .

## بنائی یا بلوک بتنی

۵- بالای دروینجره و سایر مللهاي باز در دیوار وسط روح فوند اسپیون که دیوار روی آن قرار میگیرد باید با استفاده از زورق گالوانیزه یا مواد هورد قبول دیگر پوشانیده شود تا آبرا بخارج دیوار شدایت نموده و رطوبت داخل بین دیوار و دروینجره نگردد.

۶- تهیچگونه ریزش ملات بداخل جدارین دیوارها مجاز نمیباشد. برای جلوگیری از ریزش ملات میتوان از چوب یا تسمه با عرضی مساوی با جدارین دیوارها استفاده نمود تا ملاتها ریخته شده در روی آن جمع آوری و سپس خارج گردد.

## ز - تعصیر و نظافت

۱- وصله کاری و تعصیر بند های بلوک چینی و یا پرگردن سوراخهای باید با ملات تازه صورت گیرد.

۲- باید وقت شود که سطح بلوک با ملات آلوهه و آفته نگردد.

۳- گلیه تکه های ملات که به آجر چسبیده اند باید پس از خشک شدن کامل ملات با استفاده از ماله و یا برس برداشته شوند.

ح - محافظت بلوک چینی : کارهای بتنی باید در صورت لزوم با استفاده از زورقها نایلونی و یا پوششها قابل قبول دیگر در مقابل برف و باران و هرگونه

عوارض جوی محافظت شوند. در رهای سردگه امکان بخ بندان میروند کارهای بلوک بتنی باید پوشانیده شده و در صورت لزوم تراست داده شوند بطوریکه حرارتی بحداقل ۵ درجه سانتیگراد بحدت ۷ ساعت پس از بلوک چینی تائیین گردد. در رهای گرم کارهای بلوک بتنی باید بعدت کافی مرتبه "مرطوب نگاهداشته شود.

## قسمت شفتم

### بنائی با سنگ

#### ۱-۷ کلیات

الف - حرارت لازم : انجام هرگونه بنائی با سنگ در موافقیکه گرمای هوای محل کار و یا درجه حرارت هریک از موارد مصرفی ازه درجه سانتیگراد کمتر است مجاز نمیباشد مگراینکه وسایل کافی و مجاز برای حرارت دادن یا عایق نمودن محل و یا موارد مصرفی بکار رود بطوریکه درجه حرارت از مقدار مشخص شده بالا کاهش نیابد .

ب - آماره نمودن بستزیرین : گلیه سطوح زیرین که بنائی بر روی آن آغاز میشود باید کاملاً تمیز شده و قبل از شروع کار مرطوب گردد .

#### ج - ملات

۱- ملات مصرفی در بنائی با سنگ باید ملات سیمانی از نوع مشخص شده باشد

۲- ملات را باید بیش از اند ازه جلوتر از محمل کار پخش نمود تا ملات قبل از قرار دادن آجر سفت نگردد .

۳- ملات باید گلیه فضای خالی بین سنگها را پر نماید .

۴- ملات سخت شده که امز روی داریست ، کف ، و یا از محلهای دیگر برداشته شده باشد باید مورد استفاده قرار گیرد .

#### ۲-۷ بنائی با سنگهای تراشیده

الف - تعریف : سنگ چینی چه بصورت منظم در رگه های یکنواخت و چه

## بنائی با سنگ

بصورت پراکنده باید با سنگهای ساخته شود که دریک بتنهای به ابعاد دقیق مورد نظر در نقشه ها یا مشخصات تراشیده آماده شده باشند و با درنظر گرفتن جزئیات درستی از ملات نصب گردند.

**ب - خیساندن سنگ** : هر سنگ باید قبل از نصب کاملاً تمیز گردیده در آب خیسانده و اشیاع گردد.

## ج - ترتیب قراردادن سنگها

- ترتیب و جزئیات کارگذاری سنگها و طریقه قفل و بست نمودن آن باید مطابق نقشه ها و یا دستورات مهندس ناظر باشد.

سنگها (غیر از سنگ نما) باید طوری کارگذاری شوند که بند عمودی رگهای متواالی دریک امتداد قرار نگیرند.

## د - سنگ چینی

۱- سنگ چینی باید کاملاً منطبق بر ترازها و ابعاد نشان داده شده انجام شود بطوریکه طریقه کارگذاری ، قفل ، بست و خامس لایه ملات دریند های افقی و قائم بشکل خواسته شده باشد.

۲- سنگ باید در محل خواسته شده طبق نقشه قرارداده شده و بخوبی در داخل ملات زیرین جایگزاري گردد.

۳- سنگ نباید بر روی دیوار پرتاپ و یا کشیده شود . بلکه باید با دقیق در محل مربوطه نصب شود بطریقی که سنگهای کارگزاری شده جایجا نشوند.

۴- سنگ چینی باید بطور یکنواخت انجام شود بطوریکه در هر زمان هیچ قسمت از یک دیوار بیش از یک ستراز قسمتهای دیگران بالاتر نباشد.

بنائی باسنگ

۵- در سنگ چینی باید دقت گردد که سطح نمای سنگ به ملات آفته نگردد.

ه- قفل و بست در کارهای بنائی با سنگ

۱- در موقع لازم باید میله مهارویا سایروسیله مهارقابل قبول به اندازه های مشخص شده در نقشه هادرد داخل سنگ چینی کارگزار شده و در محل تثبیت گردد. سوراخهای لازم برای قراردادن مهارها باید قبل از نصب سنگ در آن تعییه شده و سنگ زیرین باید فقط پس از کارگزاری سنگ سوراخ شده فوکانی سوراخ گردد و تا اطمینان حاصل گردد که سوراخهای ریک امتداد قرار خواهند گرفت.

۲- در موقعیکه سنگ چینی در مجاورت ستون بتی و یا فلزی قرار میگیرد مهارهای فلزی از نوع و بشکل خواسته شده باید در داخل ملات قرار داده شده و انتهای آن در داخل ستون مهارویا با آن جوش شود.

و- مشخصات بند در سنگ چینی

۱- ضخامت بند های باید کاملاً مساوی بوده و هیچگاه از ۰.۱ میلیمتر کمتر و از ۰.۲ میلیمتر بیشتر نباشد.

۲- بجز در موارد یکه بند کش باید جداگانه صورت گیرد کلیه بند های نما باید قبل از سخت شدن ملات با استفاده از وسائل مناسب بند کش گردد.

۳- بند هاییکه بعد ا بند کش میشود باید قبل از سخت شدن ملات

## بنائی با سنگ

بعمق لازم از ملات خالی گردد.

ز - سایر طرزات : مقررات مربوطه برای بنائی با آجر که در مرور سنگچینی نیز صادر است باید رعایت گردد.

## ۳-۷ بنائی با سنگ لاشه

الف - تعریف : لاشه چینی چه بصورت منظم در رگهای تاحدود ممکنه دارا ی سطوح چهارگوش است و گوشه های تیز و نامناسب آن تراشیده شده انجام شود. در این نوع بنائی از ملات بعنوان لایه چسبنده استفاده میگردد.

ب - خیساندن سنگ : هر سنگ باید قبل از نصب کاملاً تمیز گردیده و در آب خیسانده گردد.

ج - ترتیب قراردادن سنگها سنگها باید بطريقی قرارگیرند که هیچیک از بند های عمودی در ج پیاپی، رویهم قرار نگیرد.

## د - لاشه چینی

۱ - لاشه چینی باید تاحدود امکان در رگهای منظم وافقی صورت گیرد و خاصمت بندها باید حتی الامکان مساوی باشد.

۲ - سنگهای رگهای زیرین باید درشت بوده و خصوصاً "انتخاب شده باشند".

۳ - سنگ باید در محل خواسته شده طبق نقشه قرارداده شده و بخوبی

در داخل ملات زیرین جایگزاري گردد.

## بنائی با سنگ

### ۴- بنائی با سنگ بصورت خشکه چینی

الف - تعريف : خشکه چینی چه بصورت منظم در رگهای ایکنواخت و چه بصورت پراکنده باید با استفاده از سنگهایی که تاحدود ممکنه دارای سطوح چهارگوش است و گوشهای تیز و نامناسب آن تراشیده شده‌اند و استفاده از ملات انجام شود.

#### ب - خشکه چینی

۱ - خشکه چینی باید تاحدود امکان در رگهای منظم وافقی صورت گیرد و ضخامت بند‌ها باید حتی الامکان مساوی باشد.

۲ - سنگهای رگهای زیرین باید در رشت و خصوصاً "انتخاب شده‌باشند".

۳ - سطوح اتنکاء هر رگ باید موازی سطوح طبیعی سنگها باشد.

۴ - هر سنگ باید در حداقل سه نقطه بر روی سطح زیرین اتنکاء داشته باشد.


#### ج - مشخصات بند در خشکه چینی

۱ - ضخامت متوسط بند‌ها در سنگ چینی نباید بیش از ۳ میلیمتر و سطح نما نباید بیش از ۵ میلیمتر باشد.

۲ - در مواقعي که چنین خواسته شده باشد در روزهای باز سطوح عقبی دیوار و یا سایر قسمتهاي سنگی باید با پاشیدن ملات پر گردد تا از نفوذ آب در روزها جلوگیری گردد.



GENERAL-TECHNICAL SPECIFICATIONS  
OF  
MASONRY



C. Joints

1. The average thickness of joints shall not exceed 30 mm and face joints shall not exceed 25 mm in width.
2. When so required or shown, open joints on the rear faces of walls or other structures shall be slushed thoroughly with mortar in order to prevent seepage of water through the joints.

2. Bottom courses shall be composed of large, selected stones.
3. Each stone shall be well settled into its place in a full bed of freshly made mortar.

#### 7.4 DRY RUBBLE MASONRY

- a. Description: Dry rubble masonry, coursed or random, shall consist of roughly squared and dressed stone laid without mortar.
- b. Laying Stone
  1. The masonry shall be laid to lines and as far as practicable in level courses and the thickness of joints shall be kept roughly uniform.
  2. Bottom courses shall be composed of large, selected stones.
  3. The bearing beds in all courses shall be parallel to the natural bed of the material.
  4. Each stone shall take a firm bearing at not less than three points upon the underlying courses.

## STONE MASONRY

2. Unless subsequent pointing is specified, face joints shall be properly tooled before the mortar sets.
  3. Joints which are to be pointed later shall be raked to a required depth before the mortar has set.
- g. Other Requirements: The relevant requirements set forth for brick masonry shall be observed in ashlar masonry construction.

### 7.3 MORTAR RUBBLE MASONRY

- a. Description: Mortar rubble masonry, coursed or random, shall consist of individual stones, roughly squared by removing unacceptable edges or projections, and laid in cement mortar.
- b. Soaking of Stones: Each stone shall be cleaned and thoroughly wet being set in place.
- c. Arrangement of Stones: Stones shall be arranged in a manner that no vertical joint shall be directly above each other.
- d. Laying Stones
  1. The masonry shall be laid to line and as far as practicable in level courses and the thickness of mortar joints shall be kept roughly uniform.

## STONE MASONRY

stones already laid.

4. Stonework shall be carried up in a uniform manner such that no portion of wall shall be raised more than 1 meter above another portion at any time.
5. Stones shall be laid in a manner that the face surfaces of stones shall not be smeared with mortar.

e. Anchorage

1. Where required, dowels or other approved ties shall be placed in the stones and firmly set by means of lead or other approved materials. Dowel holes shall be drilled through each stone before the stone is placed and drilling of the underlying course shall be performed after the superior stone is placed on top, to assure proper alignment of the holes.
2. Where stonework is placed against concrete or steel columns, metal ties of approved design shall be placed in the mortar and anchored in or welded to the adjacent concrete or steel column respectively.

f. Joints

1. The thickness of joints shall be uniform and shall be not less than 10 mm nor more than 25mm.

## 7.2 ASHLAR MASONRY


- a. Description: Ashlar masonry, coursed or random, shall consist of individual stones, dressed or tooled to exact dimensions shown on the drawings or as otherwise specified, and placed in a bed of mortar according to the details.
- b. Soaking of Stones: Each stone shall be cleaned and thoroughly saturated with water before being set in place.
- c. Arrangement of Stones

The arrangement of courses and bond shall be as indicated on the drawings, or as directed by the Engineer. Stones shall be arranged in a manner that there will be no consecutive vertical joints.
- d. Laying Stones
  1. Stones shall be laid to exact lines and levels to ensure the required bond and thickness of mortar in beds and joints.
  2. Each stone shall be well bonded, laid on required place, and solidly settled into freshly made mortar.
  3. Stones shall not be dropped on or dragged over the wall, but shall be placed without jarring.

SECTION 7  
STONE MASONRY

7.1 GENERAL

- a. Temperature Requirements: No stone work shall be done when the working temperature and/or the temperature of any of the materials is below 5°C unless adequate and approved heating or insulating facilities have been provided to maintain the aforementioned temperature requirements.
- b. Preparation of Underlying Surfaces: All underlying surfaces shall be cleaned from foreign materials and dampened before masonry work begins.
- c. Mortar
  1. Mortar stone masonry shall be constructed using cement mortar of the specified type.
  2. Mortar shall not be spread too far ahead of actual laying so as to permit stiffening or loss of plasticity.
  3. Mortar shall fill all the empty spaces between stones.
  4. Dead mortar that has been picked up from the scaffold or from the floor shall not be used.



inside the cavity and across a level of ties to catch the droppings.

g. Patching and Cleaning

1. Patching of mortar joints or filling of holes shall be done with fresh mortar.
2. Particular care shall be taken to prevent smearing of mortar into the surface of block.
3. Any mortar droppings that stick to the block wall shall be removed after drying by means of a trowel or a brush.

h. Protection: Concrete block walls shall be protected against rain or snow entering the cores by means of polystyrene sheets or other suitable covering. In cold weather where there is a possibility of freezing, concrete blockwork shall be covered and adequately heated to maintain a temperature of at least 5°C during 72 hours after placing. During hot weather, the masonry shall be sprayed with additional quantities of water.

## CONCRETE BRICK MASONRY

2. Unless otherwise shown on the drawings, neither the inner nor the outer walls shall be less than 10 cm thick, and the space between them shall be not less than 5 cm nor more than 8 cm.
3. The inner and the outer walls shall be tied together using rectangular ties made from non-corrosive wire minimum 8 mm in diameter. Ties shall be spaced not more than 50 cm vertically and 60 cm horizontally and in no event shall there be less than 4 ties each square meter of wall. Additional bonding shall be provided for at all opening and corners.
4. Where there is any possibility of water collecting in the wall, pencil-type weepholes shall be formed at the bottom of cavity walls by placing and removing well greased sash cord or rubber tubing in the vertical mortar joints. Weepholes shall be placed not more than 1.0 meter apart.
5. The heads of windows, doors and other wall openings and the bottom course of foundation, shall be flashed with non-corroding materials so that any moisture entering the wall cavity will be directed toward the outside walls.
6. No accumulation of mortar droppings shall be allowed in the cavity and a clear cavity shall be maintained by laying boards of proper size

## CONCRETE BRICK MASONRY

be well driven into the joints and finished with an approved pointing tool.

3. Joints in exterior or interior walls scheduled to receive facing, covering, or veneer shall be lightly raked to provide bond.
4. Joints in masonry surfaces which are scheduled to receive waterproofing shall be flush with masonry work.

e. Openings in Block Work

1. Window and door openings or any other opening in walls shall be built accurately using half-size or clean-cut blocks. Blocks shall be cut to the required dimensions using masonry saws or other approved means so as to obtain neat surfaces and avoid cracks or other imperfections in the blocks.
2. Around window and exterior door openings, masonry shall be kept back a sufficient distance to permit a caulked joint.

f. Concrete Block Cavity Walls: In construction of cavity walls, the following additional requirements shall be met.

1. Cavity walls shall be constructed above the outside ground level and over a solid foundation.

## CONCRETE BRICK MASONRY

2. Intersecting bearing walls and partitions shall not be tied together in a masonry bond (except at the corners), instead, the walls shall be tied together with a metal tiebar not less than 6 mm thick, 3 cm wide, and 60 cm long with 5 cm right angle bends on each end. These tiebars shall be placed not over one meter apart vertically and the cores in which the ends of tie bars are embedded shall be filled with mortar.
3. Intersecting non-bearing walls shall be tied together using galvanized wire mesh not less than 40 cm long in alternate courses.

d. Joints

1. All vertical joints shall be completely filled with mortar.
2. Joints not pointed (tooled) at the time of blockwork shall be thoroughly wetted with clean water and filled with mortar. The mortar shall

## CONCRETE BRICK MASONRY

5. Blockwork shall be carried up in a uniform manner such that no portion of wall shall be raised more than 1 meter above another portion at any time.
6. Blocks shall not be moved or straightened after mortar has fully or even partially stiffened. Final positioning of blocks shall be done while the mortar is soft and plastic.
7. Unfinished work shall be stepped back for joining with new work and should be in accordance to the item C " Bond and Anchorage ". Before new work is started all loose mortar shall be removed and the exposed joints shall be thoroughly watered.

c. Bond and Anchorage

1. Where block work is placed against concrete or steel columns, providing there is not an expansion joint, metal ties of approved design shall be placed at alternate courses and anchored in or welded to the adjacent concrete or steel columns respectively.

## 6.2 HOLLOW CONCRETE BLOCKWORK

- a. Soaking of Blocks : Each block shall be cleaned and thoroughly saturated before being set, and kept damped while being built.
- b. Laying Blocks
  1. Unless the wall is of such a thickness as to permit laying full size header blocks and except for cavity walls, the width of the blocks used for each wall shall be equal to the thickness of that wall.
  2. Blocks shall be laid perfectly horizontal with cells vertical and level courses breaking joints with the course below. The resulting block-work shall be plumb, square, and true to the dimensions shown on the drawings.
  3. Corners of the walls shall be built first, generally four or five courses higher than the course in the middle part of the wall.
  4. If hollow blocks being used in construction of bearing walls, the dequote dowels should placed in the core. Number of the required dowels and their diameters is depend upon the type of the wall and should calculated for each walls. The core of such a blocks which contains dowels should filled with 1.6 portland cements mortar, also the cores of all concrete blocks used below the final grade as well as the block course immediately under beams, slabs, or any other structural member shall be completely filled with the same mortar. The top surface of the block walls shall be kept free of mortar in order to allow bonding between the floor and the blockwork.

## SECTION 6

### CONCRETE BLOCK MASONRY

#### 6.1 GENERAL

- a. Temperature Requirements: No block work shall be done when the working temperature and/or the temperature of any of the materials, is below 5°C unless adequate and approved heating or insulating facilities have been provided to maintain the minimum temperature requirements.
- b. Preparation of Underlying Surfaces: All underlying surfaces shall be cleaned from foreign matters and dampened before masonry work begins.
- c. Mortar
  1. Mortar shall be cement mortar of the specified shall be spread fully on the solid part of the underlying surfaces and over the vertical face of the block which is to be laid.
  2. Mortar shall not be spread too far ahead of actual laying in order to prevent stiffening or loss of plasticity.
  3. Dead mortar that has been picked up from the scaffold or from the floor shall not be used.

## BRICK MASONRY

5. The heads of windows, doors and other wall openings and the bottom course of foundation shall be flashed with non-corroding materials so that any moisture entering the wall cavity will be directed toward the outside walls.
  6. No accumulation of mortar droppings shall be allowed in the cavity and a clear cavity shall be maintained by laying boards of proper size inside the cavity and across a level of ties to catch the droppings.
- i. Patching and Cleaning
    1. Patching of mortar joints or filling of holes shall be done with fresh mortar.
    2. Particular care shall be taken to prevent smearing of mortar into the surface of brick.
    3. Any mortar droppings that stick to the brick wall shall be removed, after drying, by means of a trowel or a brush.
  - j. Protection: Brick masonry shall be protected against rain or snow by means of polystyrene sheets or other suitable covering. In cold weather where there is a possibility of freezing, brick work shall be covered and adequately heated to maintain a temperature of at least 5°C during 72 hours after placing. During hot weather, the masonry shall be sprayed with additional quantities of water provided that cement mortar has been used in the work.

locations provided that no broken brick shall be part of any vertical surface of the masonry.

- h. Brick Cavity Walls: In construction of cavity walls, the following additional requirements shall be met:
1. Cavity walls shall be constructed above the outside ground level and over a solid foundation.
  2. Unless otherwise shown on the drawings, neither the inner nor the outer walls shall be less than  $\frac{1}{2}$  brick thick, and the space between them shall be not less than 5 cm nor more than 8 cm.
  3. The inner and the outer walls shall be tied together using rectangular ties made from non-corrosive wire minimum 8 mm in diameter. Ties shall be spaced not more than 50 cm vertically and 60 cm horizontally and in no event shall there be less than 4 ties in each square meter of wall. Additional bonding shall be provided for at all opening and corners.
  4. Where there is any possibility of water collecting in the wall, pencil-type weepholes shall be formed at the bottom of cavity walls by placing and removing well greased sash cord or rubber tubing in the vertical mortar joints. Weepholes shall be placed not more than 1.0 meter apart.

3. All corners of walls shall be tied in a masonry bond.

e. Joints

1. Exposed joints shall be tooled with a slightly concave pointing tool when mortar has become "thumb-print" hard.
2. Joints in exterior or interior walls scheduled to receive facing, covering, or veneer shall be lightly raked to provide bond.
3. Joints in masonry surfaces which are scheduled to receive waterproofing shall be flush with masonry work.

f. Openings in Brick Work

1. Window and door openings or any other opening in walls shall be built accurately using half-size or clean-cut bricks. Bricks shall be cut to the required dimensions using masonry saws or other approved means so as to obtain neat surfaces and avoid cracks or other imperfections in the bricks.
  2. Around window and exterior door openings, masonry shall be kept back a sufficient distance to permit a caulked joint.
- g. Use of Half-Bricks: Half bricks may be used at openings, behind the stretchers, and other approved

## BRICK MASONRY

3. Base masonry work up to 35 cm above the ground level shall be performed by especially selected solid and well backed bricks.

4. Exterior facing bricks shall be laid with backing and shall have the back parged with a full 1 centimeter layer of setting mortar so as to form a continuous coat, except when broken by bonding headers or ties.

d. Bond and Anchorage

1. Where brick work is placed against concrete or steel columns providing there is not an expansion joint, metal ties of approved design shall be placed at alternate courses and anchored in or welded to the adjacent concrete or steel columns respectively.

2. Intersecting walls shall be tied together in a masonry bond and the bond shall consist of at least 50% of the bricks, and metal angle ties of approved design shall be placed at alternate courses.

## 5.2 Masonry with Hand Made Brick


- a. Soaking of Bricks: Bricks shall be cleaned and thoroughly saturated with water before use and kept damp while being built.
- b. Arrangement of Bricks: Brick work having a thickness equal or greater than one brick length shall be built in such a way to achieve adequate interlocking. The arrangement of headers and stretchers shall be such as to produce adequate bond. In a very exceptional case with permission of Engineer block work could be of alternate headers and stretchers with consecutive courses breaking joints.
- c. Laying Bricks
  1. Bricks shall be laid perfectly horizontal with uniform joints not exceeding 12mm and not less than 10mm in thickness. The resulting brick work shall be plumb, square, and true to lines and dimensions shown on the drawings. Each brick, prior to laying, shall be buttered with mortar on its vertical faces; then, when laid, shall be shoved into place by means of a trowel.
  2. Bricks shall not be moved or straightened after mortar has fully or even partially stiffened. Final positioning of bricks shall be done while the mortar is soft and plastic.

## SECTION 5

### BRICK MASONRY

#### 5.1 GENERAL


- a. Temperature Requirements: No brick work shall be done when the working temperature and/or the temperature of any of the materials is below 5°C unless adequate and approved heating or insulating facilities have been provided to maintain the aforementioned minimum temperature requirement.
- b. Preparation of Underlying Surfaces: All underlying surfaces shall be cleaned from foreign matters and dampened before masonry work begins.
- c. Mortar
  1. Mortar shall be spread fully on the solid part of the underlying surfaces and also over the vertical faces of the brick which is to be laid.
  2. Mortar shall not be spread too far ahead of actual laying in order to prevent stiffening or loss of plasticity.
  3. Dead mortar that has been picked up from the scaffold or from the floor shall not be used.



4. The Average Compressive Strength of blocks (including hollow area) tested with the Iranian Standard ISIRI No.70 shall be not less than  $40 \text{ kg/cm}^2$
5. Appearance: The faces of blocks shall be flush true, of a uniform texture, free from cavities, stratification of aggregate, cement accumulations, stains, cracks or other defects of appearance. The edges of blocks shall be straight, sharp, and free from any defect.
6. Damage and Repair: Blocks which are damaged during transportation or at any time before laying shall be discarded. No patching up of damaged blocks shall be permitted.

#### 4.3 HOLLOW LOAD-BEARING CONCRETE BLOCKS

- a. Load-Bearing Blocks shall meet the requirements of section 4.2 with the following exceptions and /or additional requirements:
  1. The average compressive strength of blocks (including hollow area) tested in accordance with the Iranian Standard ISIRI No. 70 shall be not less than  $60 \text{ kg/cm}^2$ .
  2. The minimum thickness of the face shells shall be not less than 3.0 cm.



## MASONRY UNITS

- c. Face Bricks shall, in addition to the above-mentioned requirements, be of the color and/or design specified on the drawings and schedules and as approved by the Engineer.
- d. Handling and Storage: Bricks shall be handled carefully so as to avoid damage of any nature which may disqualify the bricks with respect to the above-mentioned requirements.

#### 4.2 HOLLOW NON-BEARING CONCRETE BLOCKS

- a. Prefabricated Concrete Blocks shall meet the requirements of ISIRI No. 70 as well as the relevant requirements set out in paragraph 4.2b below.
- b. Site-Fabricated Concrete Blocks shall meet the requirements of ISIRI No. 70 as well as the following specifications:
  - 1. Proportions of ingredients of non bearing concrete blocks should be consist of coarse sand and portland cement with ratio of 1:4 by volume, or 50kg. Portland cement and 0.17 coarse sand by weight.
  - 2. Molding and Consolidation shall be performed by block machines of approved class, rating, and manufacture.
  - 3. Mixing shall be done in mechanical mixers in accordance with paragraph 2.7.




## SECTION 4

### MASONRY UNITS

#### 4.1 CLAY BRICKS

- a. Standards and Codes: ISIRI No. 7.
- b. Nonstandardized Bricks: Local bricks which do not meet the dimensional or other requirements of ISIRI No. 7 may be used provided that the use of such bricks have been specified on the drawings or by the Engineer and that the following requirements have been met:
  1. That bricks are well baked, hard, sound, free from flaw, cracks, twists, and turns, and give a clear ring when struck together.
  2. That bricks have the required dimensions. The allowable tolerance should be according to ISIRI No. 7.
  3. That bricks have straight edges and sharp angles.
  4. That bricks have the specified compressive strengths. However, the average compressive strength of bricks shall in no event be less than  $100\text{kg/cm}^2$  and no individual brick shall have a compressive strength less than  $80\text{ kg/cm}^2$ . The compressive strength of hand made bricks shall in no event be less than  $50\text{ kg/cm}^2$ .
  5. That the absorption of bricks shall not fall beyond the specified limits.



## MASONRY MORTARS

- b. Sand-Lime Mortar shall have the mix proportions given in table 3

Table 3

TYPE	MIX PROPORTIONS		
	Sand ( $m^3$ )	Crushed Lime ( kg. )	Water ( Lit. )
1:3	0.90	174	290

- c. Lime - Cement Mortar shall have the following mix proportions given in Table 4

Table 4

TYPE	Mix Proportions				Ave. 28 days compressive strength of a sample 70X70X70 $cm^3$ ( $kg/cm^2$ )
	Washed sand ( $m^3$ )	Crushed Lime(kg )	Portland cement ( kg)	Water ( Lit. )	
1:2:8	0.91	131	131	280	25
1:2:10	0.96	110	130	275	19




## SECTION 3

### MASONRY MORTARS

#### 3.1 GENERAL

- a. Materials and Proportions: Mortar shall be made with materials of such proportions and in such a manner as to meet the strength, consistency, workability and other required properties specified hereunder and also be suitable for the intended masonry work.
- b. Strength: Mortar shall meet the minimum compressive strength requirements designated in tables 2 and 3. The strength of mortar shall be tested in accordance with the requirements set forth in ISIRI No. 20-1 and verified to the acceptance of the Engineer and in compliance with the strength requirements.
- c. Classification of Mortars  
Classification of mortars should be according to publication No. 28 of Technical Research and Standard Bureau of Plan and Budget Organization.
- d. Class Requirements: Mortar shall be of the class shown on the drawings, or other classes of contract documents.  
Mortar with 28 days compressive strength lower than  $15 \text{ kg/cm}^2$  shall be used only in interior non-structural masonry work.



## MASONRY MORTARS

Mortar with 28 days compressive strength lower than  $15 \text{ kg/cm}^2$  shall be used only in interior non-structural masonry work.

### 3.2 REQUIRED PROPERTIES OF MORTARS

- a. Sand-Cement Mortar shall have the mix proportions given in table 2 . The amount of cements is minimum requirement.

Table 2

TYPE	MIX PROPORTIONS			Min. 28 days compressive strength of a sample 70X70X70 cm <sup>3</sup> (kg/cm <sup>2</sup> )
	Washed Sand (m <sup>3</sup> )	Portland Cement(kg.)	Water ( Lit.)	
1:6	1.03	198	256	44
1:5	1.01	227	265	81
1:4	0.99	285	261	138
1:3	0.94	360	258	228

2.5 WATER

- a. Water for making any mortar containing portland cement shall meet the requirements set out in ISIRI No. 18-3
- b. Water for making mortars not containing portland cement shall be clean and free from injurious amounts of foreign matter.

2.6 TYING AND ANCHORING MATERIALS

- a. Mesh for tying (anchoring) masonry walls shall be made of minimum 3mm. thick galvanized wire and shall have openings not larger than 1.0 cm.
- b. Tie Bars (round or flat) shall be non-corroding metal of such size and design shown on the drawings or specified herein.

2.7 MASONRY STONE


- a. Ashlar Stone shall be tough, dense, sound and durable, uniform in color, and free from seams, cracks, or other structural defects, and resistant to weathering action. Stone shall be of the kind specified on the drawings or other Contract Documents. Stone shall be of such size and dimensioned proportions as required for the work and shall not be less than 20 cm. nor more than 75 cm. in thickness. Stone shall have the specified surface finish. All stone shall be dressed to exact sizes before being laid.

## MASONRY MATERIALS

- b. Rubble Stone shall be sound and durable, free from seams, cracks, or other structural defects and devoid of rounded, worn, or weathered surfaces. Stone shall have a thickness of not less than 20 cm, a width not less than  $1\frac{1}{2}$  times the thickness, and a length (except for headers) not less than  $1\frac{1}{2}$  times the width.
- c. Coping Stone shall be of the shape and dimensions shown on the drawings and shall meet the requirements set forth for ashlar stone as well as all other specified requirements.

2.8 MORTAR COLORING PIGMENTS

Pigments for coloring of mortar shall be of high purity, chemically inert, unfading and alkali-fast mineral oxides, and shall be finely ground & specially prepared for use in mortars.



- b. Additional Requirements: Aggregates for manufacturing of concrete blocks shall fall within the gradation limits shown in table No.1

TABLE No.1 GRADATION LIMITS OF AGGREGATE FOR CONCRETE BLOCKS


Sieve No.	Sieve Size (mm)	Percent Passing (by weight)
3/8	9.520	100
4	4.760	65-90
8	2.380	35-65
16	1.190	23-52
30	0.590	15-38
50	0.297	10-25
100	0.149	2-5
200	0.075	0-3

- c. Storage: Of aggregates shall be as specified in paragraph 2.2b above.

#### 2.4 LIME

- a. Standards and Codes: ISIRI No. 270

- b. Handling and Storage: Lime shall be handled in watertight packages and shall be protected against moisture & foreign matter, and shall be used within 15 days from the time of storage. Quicklime shall be protected from exposure to sun and shall be used within 24 hours after slaking.



SECTION 2  
MASONRY MATERIALS

**2.1 MASONRY CEMENT**

- a. Standards and Codes: ISIRI No. 389 thru 395.
- b. Types of Cement: Unless otherwise specified, cement type I and II shall be used for Masonry work above and below grade respectively.

**2.2 MASONRY SAND**

- a. Standards and Codes: ISIRI No. 299
- b. Storage: Sand shall be stored in such a manner that the following conditions are met:
  1. No foreign matter shall intrude into Sand.
  2. No deterioration of Sand shall take place.

Any material which has deteriorated or damaged shall not be used for masonry work.

**2.3 AGGREGATES FOR CONCRETE BLOCKS**

- a. Standards and Codes: ISIRI No. 300 and 70

SECTION 1  
GENERAL REQUIREMENTS

**1.1 SCOPE**

Masonry works shall include the provision of all labour, materials, equipment and services and the performance of all operations required for complete execution of the works as shown on the drawings or specified herein, in accordance with the requirements of the Contract Documents, and to the full satisfaction of the Engineer.

**1.2 STANDARDS AND CODES**

All materials shall meet the requirements of the respective Iranian Standards (ISIRI) and also such additional requirements specified herein. The materials for which no Iranian Standards may be found, and/or the materials which have not been specified in these specifications, shall meet the requirements of such applicable international standards and codes as accepted by the Engineer.

**1.3 SAMPLES AND TESTS**

All materials and workmanship shall be subject to the tests indicated hereinafter or any such additional tests as may be required by the Engineer.

## GENERAL REQUIREMENTS

The Contractor shall, when so required by the Engineer, before proceeding with the works, and at his own expense, furnish for approval sufficient quantities of samples or other satisfactory evidence as to the kind and quality of materials and workmanship. Materials delivered to the Site which are in any way inferior to the approved samples or fail to meet the relevant requirements shall be rejected and removed from the Site.

#### 1.4 PREVAILANCE OF DOCUMENTS

Where the contact drawing and clauses of this specification contradict, the contractor drawings are prevail

#### 1.5 INSPECTION

The Engineer shall have free access, at all reasonable times, to inspect the materials in the mill, stockyard, shop and field. However, this shall not relieve the Contractor of his responsibilities to furnish satisfactory materials.



## SECTION 4 - MASONRY UNITS

<u>PARAGRAPH</u>	<u>DESCRIPTION</u>	<u>PAGE NO.</u>
4.1	Clay Bricks	4-1 to 4-2
4.2	Hollow Nonload-Bearing Concrete Blocks	4-2 to 4-3
4.3	Hollow Load-Bearing Concrete Blocks	4-3

## SECTION 5 - BRICK MASONRY


5.1	General	5-1
5.2	Clay Brick Work	5-2 to 5-6

## SECTION 6 - CONCRETE BLOCK MASONRY

6.1	General	6-1
6.2	Hollow Concrete Block Work	6-2 to 6-7

## SECTION 7 - STONE MASONRY

7.1	General	7-1
7.2	Ashlar Masonry	7-2 to 7-4
7.3	Mortar Rubble Masonry	7-4 to 7-5
7.4	Dry Rubble Masonry	7-5 to 7-6



## C O N T E N T

### SECTION 1 - GENERAL REQUIREMENTS


<u>PARAGRAPH</u>	<u>DESCRIPTION</u>	<u>PAGE NO.</u>
1.1	Scope	1-1
1.2	Standards and Codes	1-1
1.3	Samples and Tests	1-1 to 1-2
1.4	Pervenance of Documents	1-2
1.5	Inspection	1-2

### SECTION 2 - MASONRY MATERIALS

2.1	Masonry Cement	2-1
2.2	Masonry Sand	2-1
2.3	Aggregates for Concrete Blocks	2-1 to 2-2
2.4	Lime	2-2
2.5	Water	2-3
2.6	Tying and Anchoring Materials	2-3
2.7	Masonry Stone	2-3 to 2-4
2.8	Mortar Coloring Pigments	2-4

### SECTION 3 - MASONRY MORTARS

3.1	General	3-1 to 3-2
3.2	Required Properties of Mortars	3-2 to 3-3
3.3	Preparing, Using & Testing of Masonry Mortars	3-3



GENERAL-TECHNICAL SPECIFICATIONS  
OF  
MASONRY